

L9 ANSWER 14 OF 29 CAPLUS COPYRIGHT 2003 ACS on STN  
ACCESSION NUMBER: 1983:541496 CAPLUS  
DOCUMENT NUMBER: 99:141496  
TITLE: Textile finishing agents  
PATENT ASSIGNEE(S): Shin-Etsu Chemical Industry Co., Ltd., Japan  
SOURCE: Jpn. Kokai Tokkyo Koho, 6 pp.  
CODEN: JKXXAF  
DOCUMENT TYPE: Patent  
LANGUAGE: Japanese  
FAMILY ACC. NUM. COUNT: 1  
PATENT INFORMATION:

PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
JP 58042682	A2	19830312	JP 1981-140555	19810907
JP 63032109	B4	19880628		

PRIORITY APPLN. INFO.: JP 1981-140555 19810907

AB Water-repellent and oil-repellent finishing agents for textiles contain 50-99 parts polymers having polyfluoroalkyl groups and 1-50 parts siloxanes having epoxy, acryloyl, methacryloyl, and/or amino groups. Thus, a 40:60 cotton-polyester blend fabric was immersed in an aq. \*\*\*emulsion\*\*\* contg. 3% copolymer [ \*\*\*87302-26-9\*\*\* ] (prepd. from 4,4,5,5,6,6,7,7,8,9,9,9-dodecafluoro-8-trifluoromethylnonyl \*\*\*acrylate\*\*\* 20, Et \*\*\*acrylate\*\*\* 5, and diacetone acrylamide 5g) and 1% of 3-glycidyloxypropyl group-contg. \*\*\*siloxane\*\*\*, squeezed, dried 2 min at 110.degree., and heated 2 min at 170.degree.. The fabric had water repellency (JIS L 1079) 100, oil repellency (3 M) 100, and good hand.

EV979440213